

[TERRA KROME Perfect Kit]

TERRA KROME Perfect Kit is a kit for perfect painting of SHOW UP TERRA KROME.

The base coat is very important for the finish of TERRA KROME. By using the KROME Primer in the kit, you can create a highly durable and glossy base coat with excellent drying properties.

KROME Primer Clear in the kit can also be used as a top coat to minimize fogging.





TERRA KROME Perfect Kit Set Content

TERRA KROME Main Agent 50g
 SHOW UP Base Color REAL BLACK (already diluted) 50g
 KROME Primer Clear 180 PRM-180 (main agent 180 g · hardener 60 g · thinner 50 g)

※1 KROME Primer Weight Ratio [Mixing Ratio 3 : 1]

PRIMER main agent	HARDENER	THINNER
100	33	10~30

TERRA KROME Perfect Kit Application

SHOW UP Base Color REAL BLACK	KROME Primer Clear main agent	Apply KROME	Topcoat with KROME Primer Clear
 <p>Thoroughly remove dusts, clean and degrease. Paint SHOW UP base color Real Black (recommended). (If you do not have one, you can also use the one-component or two-component black base color you usually use.)</p>	 <p>After it is dried, apply KROME Primer Clear. *1 Prepared by weight ratio [mixing ratio]. Apply a thin first coat, then apply the second and third coats at intervals of about 5 minutes to create a glossy finish. Be sure to dry at 20°C for at least 48 hours, or force dry at 60°C for at least 3 hours. Note) If the primer is not completely cured, KROME will become cloudy. We recommend that you apply the test piece under the same conditions to prevent failure due to insufficient drying.</p>	 <p>After KROME Primer Clear has completely cured, apply it using your airbrush or spray gun with a diameter of 0.6mm to 1.6mm. Apply a thin layer on the first and second coats to prevent splashing. Do the same thing from the third time onwards, don't apply too thickly, apply a thin layer evenly over the whole area. As it begins to dry, a plating effect will gradually appear. Once the plating is completely exposed, apply the next coat on top. The number of times you should apply the paint is 3 to 6 times. After painting, dry at 20°C for at least 24 hours and at 60°C for at least 1 hour. Note) Insufficient drying may cause cloudiness after top coat.</p>	 <p>Top coat with KROME Primer Clear. *1 Prepared by weight ratio [mixing ratio]. Apply a thin layer of KROME paint to cover the entire surface. Note) Please do not over spray from the first coat, this will cause the paint to smear. 1st spray paint → dry for 10 minutes → 2nd wet paint → dry for 5 minutes → 3rd coat gives a glossy finish to complete. After drying at 20°C for 24 hours or more and forced drying at 60°C for 1 hour, it can be polished like commercially available clears.</p>

*For GOLD KROME (gold plating), SHOW UP Gold Krome Kandy series/GOLD (gold plating), COPPER (copper plating), ROSE (pink gold plating) after painting with TERRA KROME and drying(24 hours or more at 20°C, 1 hour or more at 60°C) Apply layers until the desired color is achieved. After drying (20°C or more) finish with KROME Primer Clear (at least 24 hours at 60°C for at least 1 hour).

